

SMART-X[®]
SMART-X[®]
GENERAL

Property	Method	Unit	5 mm	10 mm	19 mm
Weight of sheet (nominal)		kg/m ²	1.00	1.90	3.00

MECHANICAL

Property	Method	Unit	5 mm	10 mm	19 mm
Flexural strength	ISO 178	MPa	10	7	5
E-modulus (in flexure)	ISO 178	MPa	600	400	200

THERMAL

Property	Method	Unit	5 mm	10 mm	19 mm
Max. service temperature	-	°C		up to 70	
Coefficient of linear expansion	ISO 11359	mm/(mK)		0.08	

 100% homogeneous polystyrene – recyclable

NOTA: Le informazioni e i dati riportati sono comunicati in buona fede e ritenuti corretti. Tuttavia essi non implicano alcuna responsabilità, garanzia, obbligo e concessione di licenze in quanto puramente indicativi. Le caratteristiche qui menzionate non costituiscono specifiche contrattuali e possono essere variate senza preavviso. Documento fornito in copia non controllata.